DuploCOLL® 3720

Double-sided adhesive tape with special paper carrier for universal applications

Product construction							
	Name	Colour	Thickness [mm]				
Liner	Silicone paper	yellow	approx. 0,08				
Adhesive covered side	Modified acrylic						
Carrier	Special paper	white	approx. 0,13				
Adhesive open side	Modified acrylic						
		Total thickness:	approx. 0,21				

Product advantages

- High initial and final adhesion
- Excellent resistance to ageing, weathering and UV-radiation
- Far-reaching resistance to the influence of chemicals and solvents
- The consistency of the adhesive guarantees excellent wetting of the substrate, enabling its use on highly absorbent surfaces such as textile, leather and paper.

Main application fields

- Self-adhesive preparation of polyethylene, PVC and polyurethane foams
- Splicing of paper, textiles, plastics and metal foils
- Bonding of leather, felt and cork
- Fastening of signs, face plates, holders and front covers

Product features		Applicability on		
Initial adhesion	• • •	Foam	• • 0	
Final adhesion	• • 0	Rubber	• • 0	
Dimensional stability	• o o Fabric		• • •	
Adhesion on even surfaces	• • •	Glass/Ceramics	• • 0	
Adhesion on rough surfaces	● ● ○	Wood	• • •	
Ageing resistance	• • •	High energy plastics: PVC, PC, ABS,	• • •	
Weathering resistance	• • •	Low energy plastics: PE, PP,	• • 0	
Chemical resistance	• • •	Metal	• • •	
Resistance to plasticizers	• • 0	Paper/Cardboard	• • •	
● ● very suitable ● ● ○ suitable	o suitable with reductions	○ ○ ○ not suitable		



DuploCOLL® 3720

Double-sided adhesive tape with special paper carrier for universal applications

Specific technical data*

Temperature range -40 °C to +150 °C** Peel strength on polypropylene after 24 h at room temperature 21 N/25 mm

Certified and recognized according to UL 969 恥

Peel strength on polyethylene after 24 h at room temperature

Technical Data

on stainless steel at +23 °C +/- 2°C Shear strength 40 N/625 mm² Peel strength 180° on stainless steel at +23 °C +/- 2°C 30 N/25 mm



17 N/25 mm

Application

18 °C to 35 °C Recommended application temperature

www.lohmann-tapes.com **Application guidelines**

Storage

Adhesive tapes should be stored at room temperature and normal humidity (50-70 %).

The storage stability is one year after delivery.

Product presentation								
Converted product	Rolls		Spools					
Width [mm]	>6	> 15	> 19	on request				
Length [m]	50/100	200	300					
Max. log width: 1260 mm Other dimensions, die-cuts and sheets on request.								

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.



^{*} Specific test results, statistically not approved.
** Reached temperature in a rising heat test.

DuploCOLL® 3720

Double-sided adhesive tape with special paper carrier for universal applications

IMPORTANT NOTE

The physical characteristics contained in this data sheet represent typical or average values. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. Many factors beyond our control and uniquely within buyer's knowledge and control can affect the use and performance of our tape in a particular application. EXCEPT AS EXPRESSIVELY AGREED IN WRITING WE DO NOT TAKE OVER ANY WARRANTY OR LIABILITY FOR THE SUITABILITY OR USABILITY OF OUR TAPES FOR CERTAIN PURPOSES AND APPLICATIONS RESULTING FROM BUYER'S SPECIAL USAGE OF THE TAPES. EXCEPT WHERE PROVIDED BY MANDATORY LEGAL PROVISIONS, WE WILL NOT BE LIABLE FOR ANY DIRECT OR INDIRECT MATERIAL OR IMMATERIAL LOSSES OR DAMAGES ARISING FROM THE USAGE OR APPLICATION OF OUR TAPES. Solely the buyer is responsible for determining the suitability of the specific tape for its use in connection with his method of application. Please consult our Technical Applications Department for specific advice.

Date of issue: July 2017



Phone: + 49 (0) 26 31 34 - 0

Fax: + 49 (0) 26 31 34 - 6661

E-mail: info@lohmann-tapes.com

